



Your Chemical Solutions Provider

**TECHNICAL DATA SHEET
TT-E-515A QUICK DRY
LUSTERLESS ALKYD ENAMEL
PAGE 1 OF 2**

PRODUCT: An air dry, lusterless alkyd enamel formulated for use on primed exterior and interior metal and wood surfaces. This enamel is low "VOC" as well as lead and chromate free, and has a quick dry time.

PROPERTIES: COLORS..... Fed Std. 595B
VOLATILE ORGANIC COMPOUNDS..... 420 G/L Maximum
GLOSS..... 6 Maximum
VISCOSITY(Reduced)..... 70 KU Maximum

DRYING TIME-AT 75 DEGREES F:

SET-TO-TOUCH..... Within 6 MINUTES
TACK FREE..... Within 10 Minutes
DRY HARD..... Within 15 Minutes After Tack Free
DRY THROUGH..... Within 48 Hours

ADVANTAGES: (1). Interior / Exterior Use
(2). Lusterless Finish
(3). Meets TT-E-515A
(4). Full Color Range, 595 Colors

USES: (1). Steel
(2). Machinery
(3). Tanks
(4). Wood
(5). Equipment
(6). Towers



Your Chemical Solutions Provider

**TECHNICAL DATA SHEET
TT-E-515A QUICK DRY
LUSTERLESS ALKYD ENAMEL
PAGE 2 OF 2**

APPLICATION & REDUCTION:

Chemsol's TT-E-515A Enamels can be applied by conventional or airless spray application. For spraying, thin up to 10% or as needed with Xylene. For brushing, use as is or with minimum thinning with TT-T-306C Type I Reducer.

SURFACE PREPARATION:

Surface must be clean, dry and free of all contamination before application. Prime and apply topcoat per specification instructions. If used on previously painted surfaces, coating must be reduced and tested on a small area for compatibility with the existing coating.

STEEL:

Surface must be clean and free of all oil, grease and foreign material. Badly rusted or pitted steel should be cleaned by commercial sandblasting and primed the same day.

PRECAUTIONS:

Contents are FLAMMABLE.
Keep away from heat and open flame.
KEEP OUT OF THE REACH OF CHILDREN.
Do not take internally.
Avoid breathing vapor or mist.
Do not use in tank or pit without proper protection.
Read Material Safety Data Sheet before use of this product.